

COMPREHENSIVE ASBESTOS INSPECTION REPORT



prepared for

Security Properties, Inc.
701 Fifth Avenue, Suite 5700
Seattle, Washington 98101
Brandon Musser

PREPARED BY:

*Bureau Veritas
6021 University Blvd., Suite 200
Ellicott City, MD 21043
800.733.0660
bvna.com*

BV CONTACT:

*Deirdre Fontaine
Expanded Services Specialist
800.733.0660 x7296337
Deirdre.Fontaine@bureauveritas.com*

BV PROJECT #:

164621.23R000-01A.086

DATE OF REPORT:

September 9, 2024

ON SITE DATE:

August 21 – 23, 2024

COMPREHENSIVE ASBESTOS INSPECTION REPORT

Franklin Commons
962 Franklin Commons Drive
Franklin, Ohio 45005

TABLE OF CONTENTS

- 1. **Executive Summary** 1
- 2. **Certification**..... 2
- 3. **Survey Scope**.....3
 - 3.1. Limitations to the ACM Survey 3
 - 3.2. Survey and Sample Collection Procedure..... 3
 - 3.3. Summary of Laboratory Results 4
 - 3.4. Discussion 9
- 4. **Conclusions and Recommendations** 10
 - 4.1. Recommendations 10
- 5. **Appendices** 11



1. Executive Summary

Bureau Veritas performed a Comprehensive Pre-Renovation Asbestos Inspection, that included on site observations of the accessible areas of Franklin Commons (the "Project"), on August 21 – 23, 2024. The Project is located at 962 Franklin Commons Drive in Franklin, Ohio 45005 which consists of twenty, two-story residential buildings with 114 apartments built in 1976 and total of approximately 94,500 square feet.

The following summarizes the independent conclusions representing Bureau Veritas' best professional judgment based on information and data available to us during the course of this assignment. Factual information regarding operations, conditions, and test data provided by the Client, owner, or their representative has been assumed to be correct and complete. Additionally, the conclusions presented are based on the conditions that existed at the time of the assessment.

Bureau Veritas collected and analyzed seven hundred seventeen (717) bulk samples from 113 homogenous sampling areas, with laboratory analysis of bulk samples showing asbestos to be present (>1% by weight) in forty (40) samples. Asbestos-containing materials include 4th layer black mastic associated with 3rd layer of white floor tile in buildings 6, 7, 8, 9, 13, 15, 16 and 19, gray floor tile and associated black mastic in building 18, yellow/black mastic associated brown/beige floor sheeting in buildings 1, and 9 6th layer of black mastic associated with 5th layer of white floor tile in buildings 1, 8, 11, 12, 13, 14, 15, 16, 17, 18 and 20, 4th layer of black mastic associated with 3rd layer of floor sheeting in building 2, yellow/black mastic associated with gray floor sheeting in buildings 3, 6, 7, 8, 12, 13, 18 and 20, black mastic associated with gray flooring sheeting in building 4, 8th layer of black mastic associated with 7th layer of white floor tile in buildings 5 and 9. Non-asbestos materials include drywall and joint compound, new floor sheeting and associated mastic, base board mastic, caulking around exterior door jambs and roofing materials.



2. Certification

Bureau Veritas has completed an Asbestos Inspection of Franklin Commons (the "Project"), located at 962 Franklin Commons Drive in Franklin, Ohio 45005. The inspection was performed at the Client's request using the methods and procedures consistent with good commercial and customary practice designed to conform to acceptable industry standards.


This report has been prepared for and is exclusively for the use and benefit of the Client identified on the cover page of this report. The purpose for which this report shall be used shall be limited to the use as stated in the contract between the client and Bureau Veritas.

This report, or any of the information contained therein, is not for the use or benefit of, nor may it be relied upon by any other person or entity, for any purpose without the advance written consent of Bureau Veritas. Any reuse or distribution without such consent shall be at the client's or recipient's sole risk, without liability to Bureau Veritas.

The independent conclusions represent our professional judgment based on information and data available to us during the course of this assignment. Factual information regarding operations, conditions, and test data provided by the Client or their representative has been assumed to be correct and complete. The conclusions presented are based on the data provided, observations, and conditions that existed on the date of the on site visit.


If you have any questions regarding this report, please contact Deirdre Fontaine at (800) 733-0660, Ext. 6337.

Inspected by:



John Ilich
State of Ohio Asbestos Hazard Evaluation Specialist (ES34450)

Prepared by:



Deirdre Fontaine
Expanded Environmental Services Specialist
Bureau Veritas

3. Survey Scope

This survey was conducted at the request of the Client for the purpose of identifying asbestos-containing materials (ACM) throughout the Project in the area(s) to be affected by the renovation.

A Licensed Asbestos Building Inspector visually inspected the building for suspect ACMs. Methodologies used were generally consistent with USEPA publications: "Guidance for Controlling Asbestos Containing Materials in Buildings" (June 1985) and "Asbestos in Buildings: Simplified Sampling Scheme for Friable Surfacing Materials" (dated October 1985). The documents were used for their asbestos survey concepts, such as identifying homogeneous materials, quantifying materials, and evaluating friability (potential to crumble with hand pressure) and condition (good, damaged). Over 3,000 products are currently known to contain asbestos. Although no comprehensive list of asbestos containing materials exists, Bureau Veritas utilized the USEPA's "Sample List of Suspect Asbestos-Containing Materials" as a general guide to identify and document suspect asbestos containing materials within the building. In addition, in some cases, the Bureau Veritas inspector utilized their experience and the knowledge obtained through training courses to identify suspect asbestos containing materials.

3.1. Limitations to the ACM Survey

Bureau Veritas inspected all reasonably accessible spaces of the building including 100% of resident units during two testing events of August 28, 2023, and August 21-23, 2024. August 28, 2023, report can be found appended to this report.

Suspected ACM subsequently identified or encountered in non-functional, inaccessible areas during demolition should be assumed to contain asbestos unless testing confirms otherwise.

3.2. Survey and Sample Collection Procedure

The Asbestos Inspection was performed on August 21 – 23, 2024. The inspection consisted of a walk-through and visual observations of the accessible interior and exterior areas for suspect ACM, assessing the ACM for condition, potential for disturbance, friability, and quantity, and the collection of bulk samples and interviews with facility personnel.

The Project consists of a of twenty, two-story residential buildings with 114 apartments built in 1976 and total of approximately 94,500 square feet.

Samples of suspect ACM were taken in accordance with Environmental Protection Agency (USEPA) protocol and were collected by John Ilich who is a State of Ohio Asbestos Hazard Evaluation Specialist. A total of seven hundred seventeen (717) samples were collected from 113 homogenous areas. All samples were transported for analysis to Schneider Laboratories Global, Inc., which is accredited by the American Industrial Hygiene Association (AIHA) and successfully participates in the National Voluntary Laboratory Accreditation Program (NVLAP). Rigorous chain-of-custody guidelines were followed to ensure proper handling and delivery of the samples.

Polarized Light Microscopy (PLM) techniques were used to analyze the samples.

The samples were analyzed for asbestos by polarized light microscopy (PLM) in accordance with the "EPA Method for the Determination of Asbestos in Bulk Building Materials." Analysis was performed by using the bulk sample for visual observation and slide preparation, and for microscopic examination and identification. The samples were mounted on slides and then analyzed for asbestos (chrysotile, amosite, crocidolite, anthophyllite, actinolite/tremolite), and fibrous non-asbestos constituents (mineral wool, fiberglass, cellulose, etc.). Asbestos was identified by refractive indices, morphology, color, and signs of elongation. The same characteristics were used to identify the non-asbestos constituents. The microscopist visually estimated relative amounts of each constituent by determining the volume of each constituent in proportion to the total volume of the sample, using a stereoscope.

During the inspection, location and friability of each suspect material were recorded.

3.3. Summary of Laboratory Results

Sample Number	Material Description	Location	Friable	% Asbestos	Condition	Estimated Quantity
579288-064 B6-FT-1	4th Layer Black Mastic Associated With 3rd Layer of White Floor Tile	Building 6, Apartment 594	No	5% Chrysotile	Intact	280 SF
579288-067 B7-FT-1	4th Layer Black Mastic Associated With 3rd Layer of White Floor Tile	Building 7 Apartment 577	No	5% Chrysotile	Intact	435 SF
579288-070 B8-FT-1	4th Layer Black Mastic Associated With 3rd Layer of White Floor Tile	Building 8 Apartment 591	No	5% Chrysotile	Intact	435 SF
579288-074 B9-FT-2	4th Layer Black Mastic Associated With 3rd Layer of White Floor Tile	Building 9 Apartment 590 and 582	No	5% Chrysotile	Intact	220 SF in each Apartment
579288-076 B13-FT-1	4th Layer Black Mastic Associated Layer of Gray Floor Tile	Building 13 Apartment 926	No	5% Chrysotile	Intact	435 SF
579288-079 B15-FT-1	4th Layer Black Mastic Associated With 3rd Layer of White Floor Tile	Building 15 Apartment 956	No	5% Chrysotile	Intact	250 SF
579288-082 B16-FT – 1	4th Layer Black Mastic Associated With 3rd Layer of White Floor Tile	Building 16 Apartment 958 and 968	No	5% Chrysotile	Intact	250 SF in each Apartment
579288-085 B18-FT-1	Gray Floor Tile and Associated Black Mastic	Building 18 Apartment 962	No	4% Chrysotile 5% Chrysotile	Intact	155 SF
579288-088 B19-FT-1	4th Layer Black Mastic Associated With 3rd Layer of White Floor Tile	Building 19 Apartment 962	No	5% Chrysotile	Intact	155 SF
579288-103 B1-FS-1	Yellow/Black Mastic Associated with Brown/Beige Floor Sheeting	Building 1 Apartment 598, 596, and 594	No	5% Chrysotile	Intact	250 SF per Apartment
579288-105 B1-FS-3	6th Layer Black Mastic Associated With 5th Layer of White Floor Tile	Building 1 Apartment 598, 596, and 594	No	5% Chrysotile	Intact	250 SF per Apartment
579288-112 B2-FS-4	4th Layer Black Mastic Associated With 3rd Layer of Yellow Floor Sheeting	Building 2 Apartment 590, 582, 580	No	5% Chrysotile	Intact	250 SF per Apartment
579288-115 B3-FS-1	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 3 Apartment 573, 575, and 579	No	5% Chrysotile	Intact	250 SF per Apartment
579288-121 B4-FS-1	Black Mastic Associated with Gray Floor Sheeting	Building 4 Apartment 581, 583, and 585	No	5% Chrysotile	Intact	250 SF per Apartment

579288-125 B5-FS-2	8 th Layer Black Mastic Associated With 7 th Layer of White Floor Tile	Building 5 Apartment 591 and 593	No	5% Chrysotile	Intact	250 SF per Apartment
579288-132 B6-FS-3	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 6 Apartment 588	No	4% Chrysotile	Intact	250 SF
579288-136 B7-FS-1	Black Mastic Associated with Gray/Beige Floor Sheeting	Building 7 Apartment 573, 579, and 581	No	2% Chrysotile	Intact	250 SF per Apartment
579288-140 B7-FS-5	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 7 Apartment 573, 579, and 581	No	4% Chrysotile	Intact	250 SF per Apartment
579288-143 B8-FS-2	6 th Layer Black Mastic Associated with White Floor Tile And 7 th Layer Beige Floor Tile	Building 8 Apartment 585, 587, 589, and 595	No	5% Chrysotile 2% Chrysotile	Intact	250 SF per Apartment
579288-145 B8-FS-4	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 8 Apartment 593 and 599	No	2% Chrysotile	Intact	250 SF per Apartment
579288-149 B9-FS-2	Yellow/Black Mastic Associated with Beige Floor Sheeting	Building 9 Apartment 590, 588, 580, and 586	No	2% Chrysotile	Intact	250 SF per Apartment
579288-150 B9-FS-3	8 th Layer Black Mastic Associated With 7 th Layer of White Floor Tile	Building 9 Apartment 590, 588, 580, and 586	No	5% Chrysotile	Intact	250 SF per Apartment
579288-154 B11-FS-1	6 th Layer Black Mastic Associated With 7 th Layer of White Floor Tile	Building 11 Apartment 581, 585, 587, and 591	No	5% Chrysotile	Intact	250 SF per Apartment

579288-161 B12-FS-2	yellow/black mastic associated with gray floor sheeting	Building 12 Apartment 914, 918, and 922	No	4% Chrysotile	Intact	250 SF per Apartment
579288-162 B12-FS-3	6 th Layer Black Mastic Associated With 5th Layer of White Floor Tile	Building 12 Apartment 916, 920 and 924	No	5% Chrysotile	Intact	250 SF per Apartment
579288-164 B12-FS-5	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 12 Apartment 914, 918, and 922	No	4% Chrysotile	Intact	250 SF per Apartment
579288-167 B13-FS-2	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 13 Apartment 930, 932 and 934	No	4% Chrysotile	Intact	250 SF per Apartment
579288-170 B13-FS-5	6 th Layer Black Mastic Associated With 5th Layer of White Floor Tile	Building 13 Apartment 928 and 936	No	5% Chrysotile	Intact	250 SF per Apartment
579288-172 B14-FS-1	6 th Layer Black Mastic Associated With 5th Layer of White Floor Tile	Building 14 Apartment 938	No	5% Chrysotile	Intact	250 SF per Apartment
579288-178 B15-FS-1	Yellow/Black Mastic Associated with Brown Floor Sheeting	Building 15 Apartment 948 and 950	No	4% Chrysotile	Intact	250 SF per Apartment
579288-181 B15-FS-4	6 th Layer Black Mastic Associated With 5th Layer of White Floor Tile	Building 15 Apartment 946 and 952	No	4% Chrysotile	Intact	250 SF per Apartment
579288-184 B16-FS-1	6 th Layer Black Mastic Associated With 5th Layer of White Floor Tile	Building 16 Apartment 960 and 964	No	4% Chrysotile	Intact	250 SF per Apartment
579288-190 B17-FS-1	6 th Layer Black Mastic Associated With 5th Layer of White Floor Tile	Building 17 Apartment 970, 972, 974, and 978	No	5% Chrysotile	Intact	250 SF per Apartment

579288-193 B17-FS-4	Black Mastic Associated with Gray Floor Sheeting	Building 17 Apartment 976 and 980	No	2% Chrysotile	Intact	250 SF per Apartment
579288-197 B18-FS-2	6 th Layer Black Mastic Associated with 5 th Layer of White Floor Tile	Building 18 Apartment 952, 954, and 960	No	5% Chrysotile	Intact	250 SF per Apartment
579288-200 B18-FS-5	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 18 Apartment 950, 956, and 958	No	2% Chrysotile	Intact	250 SF per Apartment
579288-205 B19-FS-4	Clear/Black Mastic Associated with Tan Floor Sheeting	Building 19 Apartment 935	No	2% Chrysotile	Intact	250 SF
579288-208 B20-FS-1	Yellow/Black Mastic Associated with Gray Floor Sheeting	Building 20 Apartment 961 and 963	No	2% Chrysotile	Intact	250 SF per Apartment
579288-211 B20-FS-4	6 th Layer Black Mastic Associated With 5 th Layer of White Floor Tile	Building 20 Apartment 965, 967, 971, and 973	No	5% Chrysotile	Intact	250 SF per Apartment
579288-338 B10-FS-2	Brown/Black Mastic Associated with Gray Floor Sheeting	Building 20 Apartment 961 and 963	No	5% Chrysotile	Intact	250 SF per Apartment

The USEPA and State of Ohio define asbestos-containing materials (ACM) as those which contain greater than one percent asbestos. Of the seven hundred seventeen (717) samples that were analyzed, forty (40) were found to contain asbestos.

The following materials were sampled and were not classified as asbestos containing materials:

- White mastic associated with various cove base located in units of all 20 buildings.
- 1st and 3rd layers of white floor tile and associated yellow mastic located in homogenous areas of select units of all 20 buildings.
- Carpet mastic located in homogenous areas of select units of all 20 buildings.
- Brown/beige floor sheeting located in areas of select units of all 20 buildings.
- Yellow floor sheeting and associate mastic located in building 3.
- Roofing materials from all 20 buildings.

The results of the Bulk Sample Analysis are presented in Appendix A of this report.

3.4. Discussion

The EPA issued a regulation in the early 1970s known as the National Emission Standard for Hazardous Air Pollutants (NESHAP). Along with other issues, the intent of the regulation was to require the removal of certain airborne hazards (e.g., asbestos) prior to renovation or demolition of the buildings that contain them. Certain asbestos-containing materials (e.g., asphalt based roofing products, floor tile, and mastics) are Category I materials and are allowed to remain in the building, but the resulting asbestos-contaminated debris must be discarded in a landfill that is EPA-approved for asbestos. Other materials (known as Category II) must be removed from the facility prior to demolition.

In addition, the USEPA has defined “friable asbestos – containing material as any building material that when dry, may be crumbled, pulverized, or reduced to powder by hand pressure.” However, it is the EPA’s position that the mere presence of a friable material (e.g. pipe insulation) does not pose a health concern as long as the material is in good condition and well maintained.

4. Conclusions and Recommendations

On August 21 – 23, 2024, Bureau Veritas completed this ACM Inspection of Franklin Commons (the “Project”), located at 962 Franklin Drive in Franklin, Ohio. A total of seven hundred seventeen (717) bulk samples of suspect ACM were collected at 113 homogenous areas and analyzed for asbestos.

The following were identified as friable asbestos-containing materials identified on the property:

- No friable ACM was identified.

The following were identified as non-friable asbestos-containing materials identified on the property:

- 4th layer black mastic associated with 3rd layer of white floor tile in buildings 6, 7, 8, 9, 13, 15, 16 and 19.
- Gray floor tile and associated black mastic in building 18.
- Yellow/black mastic associated brown/beige floor sheeting in buildings 1 and 9.
- 6th layer of black mastic associated with 5th layer of white floor tile in buildings 1, 8, 11, 12, 13, 14, 15, 16, 17, 18 and 20.
- 4th layer of black mastic associated with 3rd layer of floor sheeting in building 2.
- Yellow/black mastic associated with gray floor sheeting in buildings 3, 6, 7, 8, 12, 13, 18 and 20
- Black mastic associated with gray flooring sheeting in building 4.
- 8th layer of black mastic associated with 7th layer of white floor tile in buildings 5 and 9.

The remaining materials sampled as part of this inspection were found to have no asbestos detected by laboratory analysis via PLM analysis.

4.1. Recommendations

Based on the results of the inspection, Bureau Veritas offers the following recommendations:

- If any ACMs are friable or will be rendered friable as a result of renovation or demolition activities, they should be removed by a State of Ohio certified asbestos abatement contractor prior to renovations. A State of Ohio certified Project Designer should prepare any plans or specifications for asbestos abatement projects. Any such renovation projects should be monitored by a qualified industrial hygiene firm for worker and environmental safety.
- Any ACMs that will not be disturbed should be managed in place using an Asbestos Operation and Maintenance (O&M) Program. As part of an O&M Program any contractors bidding on or performing work in the area should be made aware of the presence and locations of ACM's.
- Any repair and maintenance activities where the ACM is going to be disturbed and may release fibers must be performed by personnel with a minimum of 16 hour OSHA Class III training. Any maintenance or custodial activities where ACM may be contacted but will not likely be disturbed should be performed by personnel with a minimum of 2 hour OSHA Class IV training. All training should comply with 29 CFR 1926.1101(k)(9)(vi).
- Suspected ACM subsequently identified or encountered in non-functional, inaccessible areas during renovation or demolition should be assumed to contain asbestos unless testing confirms otherwise.

5. Appendices

- Appendix A: Laboratory Analytical Results
- Appendix B: Certifications and Accreditation
- Appendix C: Prior Baseline ACM Survey Report

Appendix A: Laboratory Analytical Results





Customer: Bureau Veritas BAPM (992)
Address: 10461 Mill Run Cir
Ste 1100
Owings Mills, MD 21117

Order #:	579288
-----------------	--------

Received 08/23/24
Analyzed 08/28/24
Reported 08/29/24

Attn:

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-001	08/21/24	B1-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Soft				
579288-002	08/21/24	B1-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Soft				
579288-003	08/21/24	B1-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Soft				
579288-004	08/21/24	B2-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Soft				
579288-005	08/21/24	B2-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Soft				
579288-006	08/21/24	B2-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Soft				
579288-007	08/21/24	B3-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Soft				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-008	08/21/24	B3-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-009	08/21/24	B3-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic Yellow, Brittle			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-010	08/21/24	B4-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-011	08/21/24	B4-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-012	08/21/24	B4-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-013	08/21/24	B5-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-014	08/21/24	B5-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-015	08/21/24	B5-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-016	08/21/24	B6-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-017	08/21/24	B6-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-018	08/21/24	B6-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Brittle			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-019	08/21/24	B7-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-020	08/21/24	B7-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-021	08/21/24	B7-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-022	08/21/24	B8-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-023	08/21/24	B8-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-024	08/21/24	B8-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-025	08/21/24	B9-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-026	08/21/24	B9-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-027	08/21/24	B9-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-028	08/21/24	B10-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-029	08/21/24	B10-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-030	08/21/24	B10-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-031	08/21/24	B11-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-032	08/21/24	B11-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-033	08/21/24	B11-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-034	08/21/24	B12-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-035	08/21/24	B12-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-036	08/21/24	B12-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-037	08/21/24	B13-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-038	08/21/24	B13-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic Beige, Brittle			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-039	08/21/24	B13-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-040	08/21/24	B14-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-041	08/21/24	B14-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-042	08/21/24	B14-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-043	08/21/24	B15-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-044	08/21/24	B15-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-045	08/21/24	B15-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-046	08/21/24	B16-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic Beige/Brown, Soft/Brittle			No Asbestos Detected	100% NON FIBROUS MATERIAL

Unable to separate individual layers.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-047	08/21/24	B16-BB-2	962 Franklin Commons DR		
Layer 1: Mastic Beige, Soft No brown mastic found.				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-048	08/21/24	B16-BB-3	962 Franklin Commons DR		
Layer 1: Mastic Beige, Soft No brown mastic found.				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-049	08/21/24	B17-BB-1	962 Franklin Commons DR		
Layer 1: Mastic White, Soft				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-050	08/21/24	B17-BB-2	962 Franklin Commons DR		
Layer 1: Mastic White, Soft				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-051	08/21/24	B17-BB-3	962 Franklin Commons DR		
Layer 1: Mastic White, Soft				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-052	08/21/24	B18-BB-1	962 Franklin Commons DR		
Layer 1: Mastic Beige, Soft No brown mastic found.				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-053	08/21/24	B18-BB-2	962 Franklin Commons DR		
Layer 1: Mastic Beige, Soft No brown mastic found.				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-054	08/21/24	B18-BB-3	962 Franklin Commons DR		
Layer 1: Mastic Beige/Brown, Soft/Brittle				No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-055	08/21/24	B19-BB-1	962 Franklin Commons DR		
Layer 1: Mastic White, Soft				No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-056	08/21/24	B19-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-057	08/21/24	B19-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-058	08/21/24	B20-BB-1	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-059	08/21/24	B20-BB-2	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-060	08/21/24	B20-BB-3	962 Franklin Commons DR		
Layer 1:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-061	08/21/24	B3-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-062	08/21/24	B3-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-063	08/21/24	B3-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-064	08/21/24	B6-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				
579288-065	08/21/24	B6-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-066	08/21/24	B6-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-067	08/21/24	B7-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				

579288-068	08/21/24	B7-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-069	08/21/24	B7-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-070	08/21/24	B8-FT-1	962 Franklin Commons DR		
Layer 1:	Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White/Blue, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				

579288-071	08/21/24	B8-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White/Blue, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-072	08/21/24	B8-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White/Blue, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-073	08/21/24	B9-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Tan, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Tan, Brittle				
	No black mastic found.				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-074	08/21/24	B9-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Tan, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			2% CHRYSOTILE	98% NON FIBROUS MATERIAL
	Black, Bituminous				
	No tan mastic found.				
579288-075	08/21/24	B9-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Tan, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-076	08/21/24	B13-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Gray, Organically Bound				
Layer 4:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				
579288-077	08/21/24	B13-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
	One floor tile found.				
579288-078	08/21/24	B13-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
	One floor tile found.				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-079	08/21/24	B15-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				

579288-080	08/21/24	B15-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-081	08/21/24	B15-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-082	08/21/24	B16-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				

579288-083	08/21/24	B16-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-084	08/21/24	B16-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-085	08/21/24	B18-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			4% CHRYSOTILE	96% NON FIBROUS MATERIAL
	Gray, Organically Bound				
Layer 2:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				

579288-086	08/21/24	B18-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile				

Not analyzed due to positive stop instructions.

Layer 2: Mastic

Not analyzed due to positive stop instructions.

579288-087	08/21/24	B18-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile				

Not analyzed due to positive stop instructions.

Layer 2: Mastic

Not analyzed due to positive stop instructions.

579288-088	08/21/24	B19-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-089	08/21/24	B19-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-090	08/21/24	B19-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-091	08/21/24	B20-FT-1	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-092	08/21/24	B20-FT-2	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-093	08/21/24	B20-FT-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-094	08/21/24	B6-CM-1	962 Franklin Commons DR		
Layer 1:	Carpet Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Brittle				
579288-095	08/21/24	B6-CM-2	962 Franklin Commons DR		
Layer 1:	Carpet Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Brittle				
579288-096	08/21/24	B6-CM-3	962 Franklin Commons DR		
Layer 1:	Carpet Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Brittle				
579288-097	08/21/24	B6-FT-4	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-098	08/21/24	B6-FT-5	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-099	08/21/24	B6-FT-6	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-100	08/21/24	B18-FT-4	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-101	08/21/24	B18-FT-5	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-102	08/21/24	B18-FT-6	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
579288-103	08/21/24	B1-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Brown/Beige, Organically Bound				
Layer 2:	Mastics			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Yellow/Black, Soft/Bituminous				

Unable to separate individual layers.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-104	08/21/24	B1-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown/Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor sheeting Beige, Org.Bound/Fibrous			No Asbestos Detected	40% CELLULOSE FIBER 60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 6:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-105	08/21/24	B1-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown/Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
579288-106	08/21/24	B1-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound No mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-107	08/21/24	B1-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound No mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-108	08/21/24	B1-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound No mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-109	08/21/24	B2-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting				

No sample in container.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-110	08/21/24	B2-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft No floor tile found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-111	08/21/24	B2-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-112	08/21/24	B2-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor sheeting Yellow, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-113	08/21/24	B2-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile Yellow, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

579288-114	08/21/24	B2-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-115	08/21/24	B3-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Unable to separate individual layers.

579288-116	08/21/24	B3-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-117	08/21/24	B3-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-118	08/21/24	B3-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Yellow, Org.Bound/Fibrous			No Asbestos Detected	40% CELLULOSE FIBER 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2:	Mastic White, Soft No yellow mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
----------	--	--	--	----------------------	---------------------------

579288-119	08/21/24	B3-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Yellow, Org.Bound/Fibrous			No Asbestos Detected	40% CELLULOSE FIBER 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2:	Mastic Yellow, Soft No white mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
----------	--	--	--	----------------------	---------------------------

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-120	08/21/24	B3-FS-6	962 Franklin Commons DR		

Layer 1:

Sample not received.

579288-121	08/21/24	B4-FS-1	962 Franklin Commons DR		
------------	----------	---------	-------------------------	--	--

Layer 1: Floor sheeting
Gray, Organically Bound

No Asbestos Detected

100% NON FIBROUS MATERIAL

Layer 2: Mastic
Black, Bituminous

5% CHRYSOTILE

95% NON FIBROUS MATERIAL

579288-122	08/21/24	B4-FS-2	962 Franklin Commons DR		
------------	----------	---------	-------------------------	--	--

Layer 1: Floor sheeting
Gray, Organically Bound

No Asbestos Detected

100% NON FIBROUS MATERIAL

Layer 2: Mastic

Not analyzed due to positive stop instructions.

579288-123	08/21/24	B4-FS-3	962 Franklin Commons DR		
------------	----------	---------	-------------------------	--	--

Layer 1: Floor sheeting
Gray, Organically Bound

No Asbestos Detected

100% NON FIBROUS MATERIAL

Layer 2: Mastic

Not analyzed due to positive stop instructions.

579288-124	08/21/24	B5-FS-1	962 Franklin Commons DR		
------------	----------	---------	-------------------------	--	--

Layer 1: Floor sheeting
Gray, Org.Bound/Fibrous

No Asbestos Detected

40% CELLULOSE FIBER
60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Mastic
Clear, Soft

No Asbestos Detected

100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-125	08/21/24	B5-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White/Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 7:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 8:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-126	08/21/24	B5-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White/Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 7:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 8:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-127	08/21/24	B5-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White/Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 7:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 8:	Mastic				

Not analyzed due to positive stop instructions.

579288-128	08/21/24	B5-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-129	08/21/24	B5-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-130	08/21/24	B6-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-131	08/21/24	B6-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Yellow, Org.Bound/Fibrous			No Asbestos Detected	40% CELLULOSE FIBER 60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Mastic White, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor sheeting Beige, Org.Bound/Fibrous No mastic found.			No Asbestos Detected	40% CELLULOSE FIBER 60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-132	08/21/24	B6-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			4% CHRYSOTILE	96% NON FIBROUS MATERIAL

Unable to separate individual layers.

579288-133	08/21/24	B6-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-134	08/21/24	B6-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-135	08/21/24	B6-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-136	08/21/24	B7-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray/Beige, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Black, Bituminous			2% CHRYSOTILE	98% NON FIBROUS MATERIAL
579288-137	08/21/24	B7-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-138	08/21/24	B7-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Org.Bound/Fibrous			No Asbestos Detected	40% CELLULOSE FIBER 60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black				

Not analyzed due to positive stop instructions.

579288-139	08/21/24	B7-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Org.Bound/Fibrous Only one layer and no mastic found.			No Asbestos Detected	40% CELLULOSE FIBER 60% NON FIBROUS MATERIAL
579288-140	08/21/24	B7-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			4% CHRYSOTILE	96% NON FIBROUS MATERIAL
579288-141	08/21/24	B7-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-142	08/21/24	B8-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-143	08/21/24	B8-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
Layer 7:	Floor Tile Beige, Organically Bound			2% CHRYSOTILE	98% NON FIBROUS MATERIAL
Layer 8:	Mastic Black, Bituminous				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-144	08/21/24	B8-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft No beige floor tile and black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL

579288-145	08/21/24	B8-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			2% CHRYSOTILE	98% NON FIBROUS MATERIAL

Unable to separate individual layers.

579288-146	08/21/24	B8-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-147	08/21/24	B8-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-148	08/21/24	B9-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound No mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-149	08/21/24	B9-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			2% CHRYSOTILE	98% NON FIBROUS MATERIAL
Unable to separate individual layers.					
579288-150	08/21/24	B9-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 7:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 8:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-151	08/21/24	B10-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

No gray sheeting floor found.

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-152	08/21/24	B10-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 7:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 8:	Mastic Black, Bituminous				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-153	08/21/24	B10-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic No gray sheeting floor found.				

Not analyzed due to positive stop instructions.

579288-154	08/21/24	B11-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-155	08/21/24	B11-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic White, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-156	08/21/24	B11-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-157	08/21/24	B11-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

579288-158	08/21/24	B11-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-159	08/21/24	B11-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-160	08/21/24	B12-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-161	08/21/24	B12-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			4% CHRYSOTILE	96% NON FIBROUS MATERIAL

Unable to separate individual layers.

579288-162	08/21/24	B12-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-163	08/21/24	B12-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

579288-164	08/21/24	B12-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			4% CHRYSOTILE	96% NON FIBROUS MATERIAL

Unable to separate individual layers.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-165	08/21/24	B12-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

579288-166	08/21/24	B13-FS1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-167	08/21/24	B13-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			4% CHRYSOTILE	96% NON FIBROUS MATERIAL

Unable to separate individual layers.

579288-168	08/21/24	B13-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-169	08/21/24	B13-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-170	08/21/24	B13-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
579288-171	08/21/24	B13-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-172	08/21/24	B14-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
579288-173	08/21/24	B14-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-174	08/21/24	B14-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Brown, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-175	08/21/24	B14-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound No mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-176	08/21/24	B14-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-177	08/21/24	B14-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft One layer found and no black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-178	08/21/24	B15-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			4% CHRYSOTILE	96% NON FIBROUS MATERIAL

Unable to separate individual layers.

579288-179	08/21/24	B15-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-180	08/21/24	B15-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-181	08/21/24	B15-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			4% CHRYSOTILE	96% NON FIBROUS MATERIAL
579288-182	08/21/24	B15-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Brown, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-183	08/21/24	B15-FS-6	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic				
	No sheeting floor found.				

Not analyzed due to positive stop instructions.

579288-184	08/21/24	B16-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Tan, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 5:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 6:	Mastic			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
	Black, Bituminous				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-185	08/21/24	B16-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

579288-186	08/21/24	B16-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-187	08/21/24	B16-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-188	08/21/24	B16-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-189	08/21/24	B16-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-190	08/21/24	B17-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
579288-191	08/21/24	B17-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-192	08/21/24	B17-FS-3	962 Franklin Commons DR		
Layer 1:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Yellow, Soft				
Layer 3:	Floor Tile			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Organically Bound				
Layer 4:	Mastic				
	No sheeting floor found.				

Not analyzed due to positive stop instructions.

579288-193	08/21/24	B17-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Gray, Organically Bound				
	One layer found.				
Layer 2:	Mastic			2% CHRYSOTILE	98% NON FIBROUS MATERIAL
	Black, Bituminous				

579288-194	08/21/24	B17-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Gray, Organically Bound				
	One layer found.				
Layer 2:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-195	08/21/24	B17-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor sheeting White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

579288-196	08/21/24	B18-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Brittle			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-197	08/21/24	B18-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL
579288-198	08/21/24	B18-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-199	08/21/24	B18-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

579288-200	08/21/24	B18-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			2% CHRYSOTILE	98% NON FIBROUS MATERIAL
Unable to separate individual layers.					
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-201	08/21/24	B18-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft No black mastic found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-202	08/21/24	B19-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-203	08/21/24	B19-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-204	08/21/24	B19-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-205	08/21/24	B19-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Clear/Black, Soft/Bituminous			2% CHRYSOTILE	98% NON FIBROUS MATERIAL

Unable to separate individual layers.

579288-206	08/21/24	B19-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-207	08/21/24	B19-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-208	08/21/24	B20-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics Yellow/Black, Soft/Bituminous			2% CHRYSOTILE	98% NON FIBROUS MATERIAL

Unable to separate individual layers.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-209	08/21/24	B20-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

Not analyzed due to positive stop instructions.

579288-210	08/21/24	B20-FS-3	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound One layer found.			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastics				

579288-211	08/21/24	B20-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic Black, Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-212	08/21/24	B20-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

579288-213	08/21/24	B20-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 3:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 4:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 5:	Floor Tile White, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 6:	Mastic				

Not analyzed due to positive stop instructions.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-214	08/21/24	B1-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-215	08/21/24	B1-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-216	08/21/24	B1-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-217	08/21/24	B2-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-218	08/21/24	B2-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-219	08/21/24	B2-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-220	08/21/24	B3-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-221	08/21/24	B3-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-222	08/21/24	B3-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-223	08/21/24	B4-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-224	08/21/24	B4-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-225	08/21/24	B4-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-226	08/21/24	B5-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-227	08/21/24	B5-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-228	08/21/24	B5-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-229	08/21/24	B6-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-230	08/21/24	B6-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-231	08/21/24	B6-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-232	08/21/24	B7-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-233	08/21/24	B7-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-234	08/21/24	B7-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-235	08/21/24	B8-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-236	08/21/24	B8-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-237	08/21/24	B8-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-238	08/21/24	B9-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-239	08/21/24	B9-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-240	08/21/24	B9-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-241	08/21/24	B10-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-242	08/21/24	B10-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-243	08/21/24	B10-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-244	08/21/24	B11-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-245	08/21/24	B11-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-246	08/21/24	B11-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-247	08/21/24	B12-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
579288-248	08/21/24	B12-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-249	08/21/24	B12-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-250	08/21/24	B13-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-251	08/21/24	B13-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-252	08/21/24	B13-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-253	08/21/24	B14-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-254	08/21/24	B14-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-255	08/21/24	B14-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-256	08/21/24	B15-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-257	08/21/24	B15-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-258	08/21/24	B15-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-259	08/21/24	B16-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-260	08/21/24	B16-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-261	08/21/24	B16-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-262	08/21/24	B17-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-263	08/21/24	B17-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-264	08/21/24	B17-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-265	08/21/24	B18-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-266	08/21/24	B18-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-267	08/21/24	B18-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-268	08/21/24	B19-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-269	08/21/24	B19-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-270	08/21/24	B19-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-271	08/21/24	B20-CK-1	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-272	08/21/24	B20-CK-2	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				
579288-273	08/21/24	B20-CK-3	962 Franklin Commons DR		
Layer 1:	Caulking			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Rubbery				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-274	08/21/24	B1-RS-1	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-275	08/21/24	B1-RS-2	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-276	08/21/24	B1-RS-3	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-277	08/21/24	B2-RS-1	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-278	08/21/24	B2-RS-2	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-279	08/21/24	B2-RS-3	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-280	08/21/24	B3-RS-1	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-281	08/21/24	B3-RS-2	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-282	08/21/24	B3-RS-3	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-283	08/21/24	B4-RS-1	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-284	08/21/24	B4-RS-2	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-285	08/21/24	B4-RS-3	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-286	08/21/24	B5-RS-1	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-287	08/21/24	B5-RS-2	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-288	08/21/24	B5-RS-3	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-289	08/21/24	B6-RS-1	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-290	08/21/24	B6-RS-2	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-291	08/21/24	B6-RS-3	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-292	08/21/24	B7-RS-1	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-293	08/21/24	B7-RS-2	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-294	08/21/24	B7-RS-3	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-295	08/21/24	B8-RS-1	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-296	08/21/24	B8-RS-2	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-297	08/21/24	B8-RS-3	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-298	08/21/24	B9-RS-1	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-299	08/21/24	B9-RS-2	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-300	08/21/24	B9-RS-3	962 Franklin Commons DR		
-------------------	----------	---------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-301	08/21/24	B10-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-302	08/21/24	B10-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-303	08/21/24	B10-RS-3	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-304	08/21/24	B11-RS-1	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-305	08/21/24	B11-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-306	08/21/24	B11-RS-3	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-307	08/21/24	B12-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-308	08/21/24	B12-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-309	08/21/24	B12-RS-3	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-310	08/21/24	B13-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-311	08/21/24	B13-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-312	08/21/24	B13-RS-3	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-313	08/21/24	B14-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-314	08/21/24	B14-RS-2	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-315	08/21/24	B14-RS-3	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-316	08/21/24	B15-RS-1	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Cement			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-317	08/21/24	B15-RS-2	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL
579288-318	08/21/24	B15-RS-3	962 Franklin Commons DR		
Layer 1:	Roofing			No Asbestos Detected	40% MINERAL/GLASS WOOL
	Black, Granular/Bituminous/Fibrous				60% NON FIBROUS MATERIAL
Sample was inhomogenous, subsamples of each component were analyzed separately.					
Layer 2:	Roof Felt			No Asbestos Detected	50% CELLULOSE FIBER
	Black, Fibrous/Bituminous				50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-319	08/21/24	B16-RS-1	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-320	08/21/24	B16-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-321	08/21/24	B16-RS-3	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-322	08/21/24	B17-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-323	08/21/24	B17-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-324	08/21/24	B17-RS-3	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-325	08/21/24	B18-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-326	08/21/24	B18-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-327	08/21/24	B18-RS-3	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-328	08/21/24	B19-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-329	08/21/24	B19-RS-2	962 Franklin Commons DR		

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-330	08/21/24	B19-RS-3	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-331	08/21/24	B20-RS-1	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-332	08/21/24	B20-RS-2	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

579288-333	08/21/24	B20-RS-3	962 Franklin Commons DR		
-------------------	----------	----------	-------------------------	--	--

Layer 1: Roofing
 Black, Granular/Bituminous/Fibrous

No Asbestos Detected

40% MINERAL/GLASS WOOL
 60% NON FIBROUS MATERIAL

Sample was inhomogenous, subsamples of each component were analyzed separately.

Layer 2: Roof Felt
 Black, Fibrous/Bituminous

No Asbestos Detected

50% CELLULOSE FIBER
 50% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-334	08/21/24	B9-FS-4	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-335	08/21/24	B9-FS-5	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-336	08/21/24	B9-FS-6	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-337	08/21/24	B10-FS-1	962 Franklin Commons DR		
Layer 1:	Floor sheeting Gray, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
579288-338	08/21/24	B10-FS-2	962 Franklin Commons DR		
Layer 1:	Floor sheetingGR Gray, Organically Bound			No Asbestos Detected	10% CELLULOSE FIBER 90% NON FIBROUS MATERIAL
Layer 2:	Mastic Brown/Black, Soft/Bituminous			5% CHRYSOTILE	95% NON FIBROUS MATERIAL

Unable to separate individual layers.

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons, ACM Survey
Location: 962 Franklin Dr, Franklin, OH
Number: 164621.23R000-01A.086

PO Number: 11208

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
579288-339	08/21/24	B10-FS-3	962 Franklin Commons DR		

Layer 1: Floor sheeting
Gray, Organically Bound

No Asbestos Detected

10% CELLULOSE FIBER
90% NON FIBROUS MATERIAL

Layer 2: Mastic

Not analyzed due to positive stop instructions.


EPA Regulatory Limit: 1%

Total layers analyzed on order: 717



Analyst **Thoria Nadiem**

579288-08/29/24 05:48 PM



Reviewed By: **Ben Wood**
Laboratory Director

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

579288

V:579\579288

SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

151d34

crites
UPS

8/23/2024 10:00:56 AM
1Z2E28998496185262

Submitting Co:	Bureau Veritas	State of Collection:		Cert. Required:	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #:	992	Phone:	800-733-0660 x6337
Ellicott City, MD 21043		Email:	Deirdre.Fontaine@bureauveritas.com		
Project Name:	Franklin Commons, ACM Survey	PO #:	11208		
Project Location:	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number:	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By:	J. Ilich				

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes				
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk <input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	Metals Total <input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	TCLP <input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP (w/ organics 10 Day)	Microbiology <input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens	
		Asbestos in Air <input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	Gravimetric <input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	Miscellaneous <input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	Sub-Contract <input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)	

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B1-BB-1	8/22/24		Boxboard Mastic (Mastic only)						
B1-BB-2									
B1-BB-3									
B2-BB-1									
B2-BB-2									
B2-BB-3									
B3-BB-1									
B3-BB-2									
B3-BB-3									
B4-BB-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 2 of 34

Submitting Co Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name Franklin Commons, ACM Survey	PO # 11208		
Project Location 962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:		
Project Number 164621.23R000-01A.086	Positive Stop; NTE 400 PLM		
Collected By J. Ilich			

Turn Around Time**	Matrix	Tests/Analytes (select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B4-BB-2	8/22/09		Basement Mastics (mastic only)						
B4-BB-3									
B5-BB-1									
B5-BB-2									
B5-BB-3									
B6-BB-1									
B6-BB-2									
B6-BB-3									
B7-BB-1									
B7-BB-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/09

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

193d34

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn-Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B7-BB-3	8/2/24		Handrails Mastic (Mastic only)						
B8-BB-1	↓		↓						
B7-BB-2									
B8-BB-3									
B9-BB-1									
B9-BB-2									
B9-BB-3									
B10-BB-1									
B10-BB-2									
B10-BB-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/2/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS!



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

12 Jul 34

Submitting Co. Bureau Veritas		State of Collection	Gen. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B11-BB-1	8/22/24		baseboard caulk (MASTIC only)						
B11-BB-2									
B11-BB-3									
B12-BB-1									
B12-BB-2									
B12-BB-3									
B12-BB-1									
B13-BB-2									
B13-BB-3									
B14-BB-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

By 5/21/34

Submitting Co. Bureau Veritas		State of Collection	Cert Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	982 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B14-BB-2	8/22/24		Baseboard Mastic (Mastic only)						
B14-BB-3	8/22/24								
B15-BB-1	8/22/24								
B15-BB-2									
B15-BB-3									
B16-BB-1									
B16-BB-2									
B16-BB-3									
B17-BB-1									
B17-BB-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 6 of 34

Submitting Co Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk <input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	Metals Total <input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	TCLP <input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP (w/ organics 10 Day)	Microbiology <input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air <input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	Gravimetric <input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	Miscellaneous <input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	Sub-Contract <input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B17-BB-3	8/28/24		Basement Mastic (MASTIC only)						
B18-BB-1	↓		↓						
B18-BB-2									
B18-BB-3									
B19-BB-1									
B19-BB-2									
B19-BB-3									
B20-BB-1									
B20-BB-2									
B20-BB-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: J. Ilich Date/Time: 8/28/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabin.com • info@slabin.com

19 Jul 34

Submitting Co: Bureau Veritas		State of Collection:	Cert. Required: <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acc# 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions: Positive Stop; NTE 400 PLM	
Project Number	164621.23R000-01A.086		
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
D3-FT-1	8/28/24		Floor Tile / mastic						
D3-FT-2									
D3-FT-3									
D6-FT-1									
D6-FT-2									
D6-FT-3									
D7-FT-1									
D7-FT-2									
D7-FT-3									
D8-FT-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: *J. Ilich*

Signature: *J. Ilich*

Date/Time: *8/28/24*

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS!



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

82 80634

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B8-FT-2	1/12/24		Floor Tile Mastic						
B8-FT-3									
B9-FT-1									
B9-FT-2									
B9-FT-3									
B13-FT-1									
B13-FT-2									
B13-FT-3									
B15-FT-1	1/12/24								
B15-FT-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: *J. Ilich* Signature: *J. Ilich* Date/Time: *1/12/24*

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 9 of 34

Submitting Co: Bureau Veritas		State of Collection:	Cont. Required: <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #: 992	Phone: 800-733-0660 x6337
Ellicott City, MD 21043		Email: Deirdre.Fontaine@bureauveritas.com	
Project Name: Franklin Commons, ACM Survey	PO #: 11208		
Project Location: 962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions: Positive Stop; NTE 400 PLM		
Project Number: 164621.23R000-01A.086			
Collected By: J. Ilich			

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B15-FT-3	8/24/14		Floor Tile Joints						
B16-FT-1									
B16-FT-2									
B16-FT-3									
B17-FT-1									
B17-FT-2									
B18-FT-3									
B19-FT-1									
B19-FT-2									
B19-FT-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/24/14

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

89 10034

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name Franklin Commons, ACM Survey	PO # 11208		
Project Location 962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions: Positive Stop; NTE 400 PLM		
Project Number 164621.23R000-01A.086			
Collected By J. Ilich			

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B20-AT-1	8/22/24		Floor Tile/masnc						
B20-AT-2	↓		↓						
B20-AT-3	↓		↓						
B6-CM-1	8/22/24		Carpet masnc						
B6-CM-2	↑		↓						
B6-CM-3	↑		↓						
B6-AT-4	↓		Floor Tile/masnc						
B6-AT-5	↓		↓						
B6-AT-6	↓		↓						
B18-AT-4	8/22/24								

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters (time in min x flow in L/min)

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabin.com • info@slabin.com

pg 11 of 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B17-F5-5	8/22/24		Floor Tile / mastic						
B18-F5-6	8/22/24		Floor Tile / mastic						
B1-F5-1	8/22/24		Floor Sheeting / mastic						
B1-F5-2	↓		↓						
B1-F5-3									
B1-F5-4									
B1-F5-5									
B1-F5-6									
B2-F5-1									
B2-F5-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS!



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

1912034

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B2-FS-3	8/22/04		Floor Sheeting / waste						
B2-FS-4									
B2-FS-5									
B2-FS-6									
B3-FS-1									
B3-FS-2									
B3-FS-3									
B3-FS-4									
B3-FS-5									
B3-FS-6									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/04

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

1913d 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B4-PS-1	8/12/24		Floor Sheeting/mastic						
B4-PS-2									
B4-PS-3									
B5-PS-1									
B5-PS-2									
B5-PS-3									
B5-PS-4									
B5-PS-5									
B5-PS-6									
B6-PS-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS!



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 14 of 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B6-FS-2	8/22/24		Floor Sheeting/masonry						
B6-FS-3									
B6-FS-4									
B6-FS-5									
B6-FS-6									
B7-FS-1									
B7-FS-2									
B7-FS-3									
B7-FS-4									
B7-FS-5									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

11150634

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification <small>(Employee, Bldg, Material, Type¹)</small>	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
D7-FS-6	8/21/24		Floor Sheeting, mastic						
D8-FS-1									
D8-FS-2									
D8-FS-3									
D8-FS-4									
D8-FS-5									
D8-FS-6									
D9-FS-1									
D9-FS-2									
D9-FS-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

Pr 16 of 34

Submitting Co:	Bureau Veritas	State of Collection:		Cert Required:	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #:	992	Phone:	800-733-0660 x6337
Ellicott City, MD 21043		Email:	Deirdre.Fontaine@bureauveritas.com		
Project Name:	Franklin Commons, ACM Survey	PO #:	11208		
Project Location:	962 Franklin Commons Drive, Franklin, OH 45005 US		Special Instructions:		
Project Number:	164621.23R000-01A.086		Positive Stop; NTE 400 PLM		
Collected By:	J. Ilich				

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B10-FS-4	8/21/24		Floor Sheeting/mastic						
B10-FS-5									
B10-FS-6									
B11-FS-1									
B11-FS-2									
B11-FS-3									
B11-FS-4									
B11-FS-5									
B11-FS-6									
B12-FS-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/21

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 17 of 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time **	Matrix	Tests/Analytes (select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B12-FS-2	8/22/24		Floor Sheeting/mastic						
B12-FS-3	↓		↓						
B12-FS-4	↓		↓						
O12-FS-5	↓		↓						
B12-FS-6	↓		↓						
B13-FS-1	↓		↓						
B13-FS-2	↓		↓						
B13-FS-3	↓		↓						
B13-FS-4	↓		↓						
B13-FS-5	↓		↓						

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min × flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 18 of 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B13-FS-6	8/21/24		Floor Sheeting/mastic						
B14-FS-1	↓		↓						
B14-FS-2									
B14-FS-3									
B14-FS-4									
B14-FS-5									
B14-FS-6									
B15-FS-1	8/22/24								
B15-FS-2	↓		↓						
B15-FS-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 19 of 34

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B15-PS-4	8/22/24		Floor Sheeting/mastic						
B15-PS-5									
B15-PS-6									
B16-PS-1									
B16-PS-2									
B16-PS-3									
B16-PS-4									
B16-PS-5									
B16-PS-6									
B17-PS-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

19 20/34

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B17-FS-2	8/22/20		Floor Sheeting/Mastic						
B17-FS-3									
B17-FS-4									
B17-FS-5									
B17-FS-6									
B18-FS-1									
B18-FS-2									
B18-FS-3									
B18-FS-4									
B18-FS-5									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/20

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 21d 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B18-FS-6	8/22/24		Floor Sweeping/master						
B19-FS-1	↓		↓						
B19-FS-2									
B19-FS-3									
B19-FS-4									
B19-FS-5									
B19-FS-6									
B20-FS-1									
B20-FS-2									
B20-FS-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 22 of 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B20-PS-4	8/22/24		Floor Sheeting/mastic						
B20-PS-5									
B20-PS-6									
B1-CK-1			Caulking						
B1-CK-2									
B1-CK-3									
B2-CK-1									
B2-CK-2									
B2-CK-3									
B3-CK-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

19 23 of 34

Submitting Co. Bureau Veritas		State of Collection	Gen. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B3-CK-2	8/22/24		CAULKING						
B3-CK-3	↓		↓						
B4-CK-1	↓		↓						
B4-CK-2	↓		↓						
B4-CK-3	↓		↓						
B5-CK-1	↓		↓						
B5-CK-2	↓		↓						
B5-CK-3	↓		↓						
B6-CK-1	↓		↓						
B6-CK-2	↓		↓						

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 24 of 34

Submitting Co.	Bureau Veritas	State of Collection		Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons, ACM Survey	PO #	11208		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:			
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM			
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B6-CK-3	8/22/24		Caulking						
B7-CK-1	↓		↓						
B7-CK-2									
B7-CK-3									
B8-CK-1									
B8-CK-2									
B8-CK-3									
B9-CK-1									
B9-CK-2									
B9-CK-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample/Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 250134

Submitting Co. Bureau Veritas		State of Collection	Gen. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name Franklin Commons, ACM Survey	PO # 11208		
Project Location 962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions: Positive Stop; NTE 400 PLM		
Project Number 164621.23R000-01A.086			
Collected By J. Ilich			

Turn Around Time**	Matrix	Tests/Analytes (Select All that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B10-CK-1	8/22/24		Caulking						
B10-CK-2	↓		↓						
B10-CK-3									
B11-CK-1									
B11-CK-2									
B11-CK-3									
B12-CK-1									
B12-CK-2									
B12-CK-3									
B13-CK-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

PI 26 of 34

Submitting Co. Bureau Veritas		State of Collection	Cert Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample#	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B13-CK-2	8/22/24		Caulking						
B13-CK-3									
B14-CK-1									
B14-CK-2									
B14-CK-3									
B15-CK-1									
B15-CK-2									
B15-CK-3									
B16-CK-1									
B16-CK-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 27 of 34

Submitting Co. Bureau Veritas		State of Collection	Gen. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B16-CK-3	8/22/24		CAULKING						
B17-CK-1	↓		↓						
B17-CK-2									
B17-CK-3									
B18-CK-1									
B18-CK-2									
B18-CK-3									
B19-CK-1									
B19-CK-2									
B19-CK-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

Pg 28 of 34

Submitting Co.: Bureau Veritas		State of Collection:	Cen. Required: <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct #: 992	Phone: 800-733-0660 x6337
Ellicott City, MD 21043		Email: Deirdre.Fontaine@bureauveritas.com	
Project Name: Franklin Commons, ACM Survey	PO #: 11208		
Project Location: 962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:		
Project Number: 164621.23R000-01A.086	Positive Stop; NTE 400 PLM		
Collected By: J. Ilich			

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B20-CK-1	8/22/20		Caulking						
B20-CK-2	↓		↓						
B20-CK-3	↓		↓						
B1-RS-1	↓		Roofing						
B1-RS-2	↓		↓						
B1-RS-3	↓		↓						
B2-RS-1	↓		↓						
B2-RS-2	↓		↓						
B2-RS-3	↓		↓						
B3-RS-1	↓		↓						

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/20

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

M 29 d 34

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B3-RS-2	8/22/24		Roofing						
B3-RS-3									
B4-RS-1									
B4-RS-2									
B4-RS-3									
B5-RS-1									
B5-RS-2									
B5-RS-3									
B6-RS-1									
B6-RS-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

Pr 30 d 34

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	982 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time **	Matrix	Tests/Analytes (select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
06-RS-3	8/22/24		Roofing						
07-RS-1	↓		↓						
07-RS-2									
07-RS-3									
08-RS-1									
08-RS-2									
08-RS-3									
09-RS-1									
09-RS-2									
09-RS-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

19 3/22/24

Submitting Co: Bureau Veritas		State of Collection	Gen. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B10-R5-1	8/22/24		Roofing						
B10-R5-2									
B10-R5-3									
B11-R5-1									
B11-R5-2									
B11-R5-3									
B12-R5-1									
B12-R5-2									
B12-R5-3									
B13-R5-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

M 320634

Submitting Co. Bureau Veritas		State of Collection	Gen. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B13-RS-2	8/22/24		Roofing						
B13-RS-3									
BM-A3-1									
B14-RS-2									
B14-RS-3									
B15-RS-1									
B15-RS-2									
B15-RS-3									
B16-RS-1									
B16-RS-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

Pa 13d34

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B16-RS-3	8/22/24		Roofing						
B17-RS-1	↓		↓						
B17-RS-2									
B17-RS-3									
B18-RS-1									
B18-RS-2									
B18-RS-3									
B19-RS-1									
B19-RS-2									
B19-RS-3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabin.com • info@slabin.com

19 34 of 34

Submitting Co. Bureau Veritas		State of Collection	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Blvd.		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons, ACM Survey	PO #	11208
Project Location	962 Franklin Commons Drive, Franklin, OH 45005 US	Special Instructions:	
Project Number	164621.23R000-01A.086	Positive Stop; NTE 400 PLM	
Collected By	J. Ilich		

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input checked="" type="checkbox"/> 3 business days <input type="checkbox"/> 5 business days <small>* not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B20-RS-1	8/22/24		Roofing						
B20-RS-2	↓		↓						
B20-RS-3	↓		↓						

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/22/24

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS

Appendix B: Certifications and Accreditation



State of Ohio
Environmental Protection Agency
Asbestos Program

Asbestos Hazard Evaluation Specialist

**John L
Ilich**



207 Robin Hood Drive
Irwin PA 15642



Certification Number Expiration Date

ES34450

9/12/24

DOB: 1/28/71

**Card not Valid
if Altered**

United States Department of Commerce
National Institute of Standards and Technology



Certificate of Accreditation to ISO/IEC 17025:2017

NVLAP LAB CODE: 101150-0

Schneider Laboratories Global, Inc.
Richmond, VA

*is accredited by the National Voluntary Laboratory Accreditation Program for specific services,
listed on the Scope of Accreditation, for:*

Asbestos Fiber Analysis

*This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2017.
This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality
management system (refer to joint ISO-ILAC-IAF Communique dated January 2009).*

2024-04-01 through 2025-03-31

Effective Dates



A handwritten signature in blue ink, reading 'Dana S. Haman', positioned above a horizontal line.

For the National Voluntary Laboratory Accreditation Program

SCOPE OF ACCREDITATION TO ISO/IEC 17025:2017

Schneider Laboratories Global, Inc.

2512 W. Cary Street
Richmond, VA 23220-5117
Ms. Jennifer Lee
Phone: 804-353-6778 X14
Email: jlee@slabinc.com
<http://www.slabinc.com>

ASBESTOS FIBER ANALYSIS

NVLAP LAB CODE 101150-0

Bulk Asbestos Analysis

Code


Description

18/A01

EPA -- 40 CFR Appendix E to Subpart E of Part 763, Interim Method of the Determination of Asbestos in Bulk Insulation Samples

18/A03

EPA 600/R-93/116: Method for the Determination of Asbestos in Bulk Building Materials



For the National Voluntary Laboratory Accreditation Program

Appendix C: Prior Baseline ACM Survey Report



September 11, 2023

Security Properties, Inc

701 Fifth Avenue, Suite 5700
Seattle, Washington 98104
Chase Olson

RE: Baseline Asbestos Survey at:
Franklin Commons
962 Franklin Commons Drive
Franklin, Ohio 45005
Bureau Veritas Project No.: 164621.23R000-001.086

Dear Mr. Olson:

Bureau Veritas has completed a Baseline Asbestos Survey that included on site observations of the accessible areas of Franklin Commons (the "Project"). The inspection was conducted by John Ilich a State of Ohio Asbestos Hazard Evaluation Specialist on August 28, 2023. The inspection consisted of a walk-through and visual observations of the accessible areas for suspect asbestos-containing materials (ACM), assessing the ACM for condition, friability, and quantity, and the collection of bulk samples. Sampling was conducted in general accordance with practices described within the ASTM Standard Practice for Comprehensive Asbestos Building Surveys Designation: E 2356-18 (ASTM E 2356-18) for Baseline Surveys. Bulk sampling was conducted on identified friable and damaged non-friable suspect ACM. Intact non-friable suspect ACM was assumed to be positive and should be sampled prior to disturbance.

Bureau Veritas inspected accessible interior areas of the Project building. The inspection was limited to interior areas consisting of all common and mechanical areas one representative tenant unit in each building. Additionally, building areas only accessible through destructive means (i.e., pipe chases and wall cavities) were not reviewed under the scope of the survey.

Summary of Results

Bureau Veritas collected and analyzed 142 bulk samples to facilitate the inspection. ACM as defined by the United States Environmental Protection Agency (USEPA) and United States Occupational Safety and Health Administration (OSHA) are materials with asbestos concentration of greater than one percent (>1%) as analyzed by PLM. Samples of suspect ACM were taken in accordance with Environmental Protection Agency (USEPA) protocol. All samples were transported for analysis to Schneider Laboratories Global, Inc., which is accredited by the American Industrial Hygiene Association (AIHA) and successfully participates in the National Voluntary Laboratory Accreditation Program (NVLAP). Rigorous chain-of-custody guidelines were followed to ensure proper handling and delivery of the samples. Polarized Light Microscopy (PLM) techniques were used to analyze the samples.

The below table details the ACM identified at the Project.

ASBESTOS-CONTAINING MATERIALS (ACM)					
MATERIAL DESCRIPTION	LOCATION	FRIABLE	% ASBESTOS	ESTIMATED QUANTITY	CONDITION
All materials samples were negative for asbestos.					

The following materials were sampled and found not to contain asbestos.

SAMPLED MATERIALS – NEGATIVE	
Yellow floor sheeting and yellow/brown mastic	Yellow floor sheeting and clear mastic
Beige floor sheeting and clear mastic	Beige floor sheeting and yellow mastic
Tan floor sheeting and clear mastic	Floor sheeting – Building 17
Floor sheeting – Building 1	Drywall and joint compound – Building 1
Floor sheeting – Building 2	Drywall and joint compound – Building 2
Drywall and joint compound – Building 3	Drywall and joint compound – Building 4
Drywall and joint compound – Building 5	Drywall and joint compound – Building 6
Drywall and joint compound – Building 7	Drywall and joint compound – Building 8

SAMPLED MATERIALS – NEGATIVE	
Drywall and joint compound – Building 39	Drywall and joint compound – Building 10
Floor sheeting – Building 11	Drywall and joint compound – Building 11
Drywall and joint compound – Building 12	Drywall and joint compound – Building 13
Drywall and joint compound – Building 14	Drywall and joint compound – Building 15
Drywall and joint compound – Building 16	Drywall and joint compound – Building 18
Drywall and joint compound – Building 17	Drywall and joint compound – Building 20
Drywall and joint compound – Building 19	

UNSAMPLED MATERIALS – ASSUMED POSITIVE	
Floating Laminate Compound	Baseboard and Mastic
Carpet Mastic	Floor tile and Mastic
Sheet Flooring	

UNSAMPLED MATERIALS – ASSUMED POSITIVE	
Floating Laminate Compound	Baseboard and Mastic
Carpet Mastic	Floor tile and Mastic
Sheet Flooring	

Please refer to the attached for supporting documentation regarding the survey including laboratory analysis results and inspector accreditations.

Based on the results of the inspection, Bureau Veritas offers the following recommendations:

- A NESHAP-compliant asbestos inspection should be conducted prior to the disturbance of suspected ACM at the Project. This inspection was performed to identify ACM at the Project. The results of this survey are not intended to be sufficient for renovation or demolition purposes.
- Any suspect material not sampled as part of this assessment should be assumed to contain asbestos until testing proves otherwise.


The independent conclusions represent our professional judgment based on information and data available to us during the course of this assignment. Factual information regarding operations, conditions, and test data provided by the Client or their representative has been assumed to be correct and complete. The conclusions presented are based on the data provided, observations, and conditions that existed on the date of the onsite visit.

This report has been prepared for and is exclusively for the use and benefit of the Client identified on the cover page of this report. The purpose for which this report shall be used shall be limited to the use as stated in the contract between the client and Bureau Veritas.

This report, or any of the information contained therein, is not for the use or benefit of, nor may it be relied upon by any other person or entity, for any purpose without the advance written consent of Bureau Veritas. Any reuse or distribution without such consent shall be at the client's or recipient's sole risk, without liability to Bureau Veritas.

If you have any questions regarding this report, please contact Deirdre Fontaine at (800) 733-0660, Ext. 7296337.

Sincerely,



Deirdre Fontaine
Expanded Environmental Services Specialist
Bureau Veritas

Attachments: Laboratory Analysis Reports
 Chain of Custody Documentation
 Inspector and Laboratory Licenses and Certifications



Customer: Bureau Veritas BAPM (992)
Address: 10461 Mill Run Cir
Ste 1100
Owings Mills, MD 21117

Order #:	530508
-----------------	--------

Received 08/30/23
Analyzed 08/31/23
Reported 08/31/23

Attn:

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-001	08/28/23	B1-FS-1	962 Franklin Commons Dr		

Layer 1: Floor sheeting
Yellow, Organically Bound
No Asbestos Detected
100% NON FIBROUS MATERIAL

Layer 2: Mastic
Yellow/Brown, Soft
No Asbestos Detected
100% NON FIBROUS MATERIAL

Unable to separate individual layers.

530508-002	08/28/23	B1-FS-2	962 Franklin Commons Dr		
------------	----------	---------	-------------------------	--	--

Layer 1: Floor sheeting
Yellow, Organically Bound
No Asbestos Detected
100% NON FIBROUS MATERIAL

Layer 2: Mastic
Yellow/Brown, Soft
No Asbestos Detected
100% NON FIBROUS MATERIAL

Unable to separate individual layers.

530508-003	08/28/23	B1-FS-3	962 Franklin Commons Dr		
------------	----------	---------	-------------------------	--	--

Layer 1: Floor sheeting
Yellow, Organically Bound
No Asbestos Detected
100% NON FIBROUS MATERIAL

Layer 2: Mastic
Clear, Soft
No Asbestos Detected
100% NON FIBROUS MATERIAL

530508-004	08/28/23	B2-FS-1	962 Franklin Commons Dr		
------------	----------	---------	-------------------------	--	--

Layer 1: Floor sheeting
Beige, Organically Bound
No Asbestos Detected
100% NON FIBROUS MATERIAL

Layer 2: Mastic
Clear, Soft
No Asbestos Detected
100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-005	08/28/23	B2-FS-2	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-006	08/28/23	B2-FS-3	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Beige, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Yellow, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-007	08/28/23	B11-FS-1	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-008	08/28/23	B11-FS-2	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-009	08/28/23	B11-FS-3	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Tan, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-010	08/28/23	B17-FS-1	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Yellow, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-011	08/28/23	B17-FS-2	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Yellow, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-012	08/28/23	B17-FS-3	962 Franklin Commons Dr		
Layer 1:	Floor sheeting Yellow, Organically Bound			No Asbestos Detected	100% NON FIBROUS MATERIAL
Layer 2:	Mastic Clear, Soft			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-013	08/28/23	B1-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall White, Powdery			No Asbestos Detected	8% CELLULOSE FIBER 92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound White, Granular			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-014	08/28/23	B1-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall White, Powdery			No Asbestos Detected	5% CELLULOSE FIBER 95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound White, Granular			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-015	08/28/23	B1-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall White, Powdery			No Asbestos Detected	8% CELLULOSE FIBER 92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound White, Granular			No Asbestos Detected	100% NON FIBROUS MATERIAL
530508-016	08/28/23	B2-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall White, Powdery			No Asbestos Detected	5% CELLULOSE FIBER 95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound White, Granular			No Asbestos Detected	100% NON FIBROUS MATERIAL

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-017	08/28/23	B2-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-018	08/28/23	B2-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-019	08/28/23	B3-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-020	08/28/23	B3-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-021	08/28/23	B3-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-022	08/28/23	B4-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-023	08/28/23	B4-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-024	08/28/23	B4-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-025	08/28/23	B5-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-026	08/28/23	B5-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-027	08/28/23	B5-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-028	08/28/23	B6-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER 92% NON FIBROUS MATERIAL
	White, Powdery				
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Beige, Granular				
Layer 3:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Dark Brown, Brittle				
530508-029	08/28/23	B6-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER 92% NON FIBROUS MATERIAL
	White, Powdery				
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
Layer 3:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Beige, Brittle				
530508-030	08/28/23	B6-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER 92% NON FIBROUS MATERIAL
	White, Powdery				
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
Layer 3:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Beige, Brittle				
530508-031	08/28/23	B7-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER 95% NON FIBROUS MATERIAL
	White, Powdery				
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-032	08/28/23	B7-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-033	08/28/23	B7-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-034	08/28/23	B8-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-035	08/28/23	B8-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-036	08/28/23	B8-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-037	08/28/23	B9-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-038	08/28/23	B9-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-039	08/28/23	B9-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	3% CELLULOSE FIBER
	White, Powdery				2% MINERAL/GLASS WOOL
	No joint compound found.				95% NON FIBROUS MATERIAL
530508-040	08/28/23	B10-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				2% MINERAL/GLASS WOOL
					96% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-041	08/28/23	B10-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-042	08/28/23	B10-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-043	08/28/23	B11-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-044	08/28/23	B11-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-045	08/28/23	B11-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-046	08/28/23	B12-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Mastic			No Asbestos Detected	100% NON FIBROUS MATERIAL
	Dark Brown, Brittle				
	No joint compound found.				
530508-047	08/28/23	B12-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
	No joint compound and mastic found.				
530508-048	08/28/23	B12-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	92% NON FIBROUS MATERIAL
	White, Powdery				8% CELLULOSE FIBER
	No joint compound and mastic found.				
530508-049	08/28/23	B13-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-050	08/28/23	B13-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-051	08/28/23	B13-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-052	08/28/23	B14-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-053	08/28/23	B14-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-054	08/28/23	B14-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-055	08/28/23	B15-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
	No joint compound found.				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-056	08/28/23	B15-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-057	08/28/23	B15-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-058	08/28/23	B16-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-059	08/28/23	B16-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-060	08/28/23	B16-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-061	08/28/23	B17-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
	No joint compound found.				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-062	08/28/23	B17-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	2% CELLULOSE FIBER
	White, Powdery				98% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-063	08/28/23	B17-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	4% CELLULOSE FIBER
	White, Powdery				96% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-064	08/28/23	B18-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-065	08/28/23	B18-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-066	08/28/23	B18-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-067	08/28/23	B19-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.

Project: Franklin Commons
Location: 962 Franklin Commons Drive
Number: 164621.23R000-001.086

PO Number: 9854

Method: EPA 600/R-93/116 & 40 CFR App. E Sub. E Pt. 763

PLM Analysis

Sample ID	Collected	Cust. ID	Location	Asbestos Fibers	Other Materials
530508-068	08/28/23	B19-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	5% CELLULOSE FIBER
	White, Powdery				95% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-069	08/28/23	B19-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-070	08/28/23	B20-DW-1	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-071	08/28/23	B20-DW-2	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				
530508-072	08/28/23	B20-DW-3	962 Franklin Commons Dr		
Layer 1:	Drywall			No Asbestos Detected	8% CELLULOSE FIBER
	White, Powdery				92% NON FIBROUS MATERIAL
Layer 2:	Joint Compound			No Asbestos Detected	100% NON FIBROUS MATERIAL
	White, Granular				

EPA Regulatory Limit: 1%
Total layers analyzed on order: 142

530508-08/31/23 04:54 PM



Analyst **Thoria Nadiem**



Reviewed By: **Mohammed Hashim**
 Microscopy Supervisor/Analyst

Reporting Limit: 1% Gravimetrically Reduced Reporting Limit: 0.01% PLM analysis is based on Visual Estimation and NESHAP recommends that any friable sample with an asbestos content less than 10 percent be verified by Point Count or TEM Analysis. The EPA recommends that any attic loose fill vermiculite should be treated as asbestos containing material. This report must not be reproduced except in full with the approval of the laboratory. The test results apply to the sample as received.



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

X 72

530508

V:\530\530508

dparker
UPS

8/30/2023 10:17:44 AM
1Z2E28999095475902

Submitting Co. Bureau Veritas		State of Collection OH	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200		Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043		Email Deirdre.Fontaine@bureauveritas.com	
Project Name	Franklin Commons	PO #	9854
Project Location	962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM	
Project Number	164621.23R000-001.086		
Collected By	J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days <small>* not available for all tests</small> <small>** past 3 PM the TAT will begin next business day</small> <small>Please schedule rush tests in advance</small>	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B1-FS-1	8/28/23		Floor sheeting for asstc						
B1-FS-2									
B1-FS-3									
B1-FS-1									
B2-FS-2									
B2-FS-3									
B11-FS-1									
B11-FS-2									
B11-FS-3									
B17-FS-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 8/28/23

ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS!



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabin.com • info@slabin.com

192/8

Submitting Co.	Bureau Veritas	State of Collection	OH	Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons	PO #	9854		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM			
Project Number	164621.23R000-001.086				
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B17-FS-2	8/28/23		Floor Sheeting/mastic						
B17-FS-3			Floor Sheeting/mastic						
B1-Dw-1			Drywall/ceiling components						
B1-Dw-2									
B1-Dw-3									
B2-Dw-1									
B2-Dw-2									
B2-Dw-3									
B3-Dw-1									
B3-Dw-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: *J. Ilich* Signature: *[Signature]* Date/Time: 8/28/23

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

P7 3/18/13

Submitting Co.	Bureau Veritas	State of Collection	OH	Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons	PO #	9854		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM			
Project Number	164621.23R000-001.086				
Collected By	J. Ilich				

Turn Around Time **	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep			<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B3-Dw3	7/28/13		Daywall Joint compound						
B4-Dw1	↓		↓						
B4-Dw2	↓		↓						
B4-Dw3	↓		↓						
B5-Dw1	↓		↓						
B5-Dw2	↓		↓						
B5-Dw3	↓		↓						
B6-Dw1	↓		↓						
B6-Dw2	↓		↓						
B6-Dw3	↓		↓						

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: *J. Ilich* Signature: *J. Ilich* Date/Time: *7/28/13*

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinç.com • info@slabinç.com

pg 4/11

Submitting Co.	Bureau Veritas	State of Collection	OH	Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200		Acct.#	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons	PO #	9854		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM			
Project Number	164621.23R000-001.086				
Collected By	J. Ilich				

Turn-Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
07-Dw1	8/28/23		Drywall Joint compound						
07-Dw2									
07-Dw3									
08-Dw-1									
08-Dw-2									
08-Dw-3									
09-Dw-1									
09-Dw-2									
09-Dw-3									
010-Dw-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 9/28/23

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabinc.com • info@slabinc.com

pg 50/8

Submitting Co. Bureau Veritas	State of Collection OH	Cert. Required <input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200	Acct # 992	Phone 800-733-0660 x6337
Ellicott City, MD 21043	Email Deirdre.Fontaine@bureauveritas.com	
Project Name Franklin Commons	PO # 9854	
Project Location 962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM	
Project Number 164621.23R000-001.086		
Collected By J. Ilich		

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP (w/ organics 10 Day)	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep			<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B10-Dw-2	8/28/23		Daywalk Joint compound						
B10-Dw-3	↓		↓						
B11-Dw-1									
B11-Dw-2									
B11-Dw-3									
B12-Dw-1									
B12-Dw-2									
B12-Dw-3									
B13-Dw-1									
B13-Dw-2									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8-28-23

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabin.com • info@slabin.com

19 6/10

Submitting Co.	Bureau Veritas	State of Collection	OH	Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons	PO #	9854		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM			
Project Number	164621.23R000-001.086				
Collected By	J. Ilich				

Turn-Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM	<input type="checkbox"/> Lead	<input type="checkbox"/> Lead	<input type="checkbox"/> BACT (MPN/PA)
		<input type="checkbox"/> PLM Qualitative	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> RCRA 8 Metals	<input type="checkbox"/> Mold Direct Exam
		<input type="checkbox"/> 400 Point Count	<input type="checkbox"/> Chromium VI	<input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> Allergens
		<input type="checkbox"/> 1000 Point Count	<input type="checkbox"/> Mercury		Sub-Contract
		<input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> _____		<input type="checkbox"/> TEM Chatfield
		Asbestos in Air	Gravimetric	Miscellaneous	<input type="checkbox"/> TEM AHERA
		<input type="checkbox"/> PCM	<input type="checkbox"/> Total Dust NIOSH 0500	<input type="checkbox"/> Silica FTIR (7602)	<input type="checkbox"/> TEM 7402
		<input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> _____	<input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B13-Dw3	8/28/13		Original for not complete						
B14-Dw1	↓		↓						
B14-Dw2									
B14-Dw3									
B15-Dw1									
B15-Dw2									
B15-Dw3									
B16-Dw1									
B16-Dw2									
B16-Dw3									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time 8/28/13

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabin.com • info@slabin.com

PA 7/18

Submitting Co.	Bureau Veritas	State of Collection	OH	Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons	PO #	9854		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM			
Project Number	164621.23R000-001.086				
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (Select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B17-Dw-1	8/28/23		Drywall joint compound						
B17-Dw-2									
B17-Dw-3									
B18-Dw-1									
B18-Dw-2									
B18-Dw-3									
B19-Dw-1									
B19-Dw-2									
B19-Dw-3									
B20-Dw-1									

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: *J. Ilich* Signature: *J. Ilich* Date/Time: *8-28-23*

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !



SCHNEIDER LABORATORIES GLOBAL, INC.

2512 West Cary Street, Richmond, Virginia 23220-5117
 804-353-6778 • 800-785-LABS (5227) • Fax 804-359-1475
 www.slabin.com • info@slabin.com

pg 8 of 8

Submitting Co.	Bureau Veritas	State of Collection	OH	Cert. Required	<input type="checkbox"/> YES <input type="checkbox"/> NO
6021 University Boulevard, Suite 200		Acct #	992	Phone	800-733-0660 x6337
Ellicott City, MD 21043		Email	Deirdre.Fontaine@bureauveritas.com		
Project Name	Franklin Commons	PO #	9854		
Project Location	962 Franklin Commons Drive, Franklin, OH 45005	Special Instructions: NTE 50 PLM			
Project Number	164621.23R000-001.086				
Collected By	J. Ilich				

Turn Around Time**	Matrix	Tests/Analytes (select ALL that Apply) Blank spaces are for additional analytes			
<input type="checkbox"/> 2 Hour * <input type="checkbox"/> Same day * <input type="checkbox"/> 1 business day <input type="checkbox"/> 2 business days <input type="checkbox"/> 3 business days <input checked="" type="checkbox"/> 5 business days * not available for all tests ** past 3 PM the TAT will begin next business day Please schedule rush tests in advance	<input type="checkbox"/> Air <input type="checkbox"/> Paint <input type="checkbox"/> Soil <input type="checkbox"/> Wipe <input checked="" type="checkbox"/> Bulk <input type="checkbox"/> Waste Water <input type="checkbox"/> Ground Water <input type="checkbox"/> Drinking Water <input type="checkbox"/> TSP / PM10 <input type="checkbox"/> _____	Asbestos in Bulk	Metals Total	TCLP	Microbiology
		<input checked="" type="checkbox"/> PLM <input type="checkbox"/> PLM Qualitative <input type="checkbox"/> 400 Point Count <input type="checkbox"/> 1000 Point Count <input type="checkbox"/> Gravimetric Prep	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Chromium VI <input type="checkbox"/> Mercury <input type="checkbox"/> _____	<input type="checkbox"/> Lead <input type="checkbox"/> RCRA 8 Metals <input type="checkbox"/> Full TCLP <small>(w/ organics 10 Day)</small>	<input type="checkbox"/> BACT (MPN/PA) <input type="checkbox"/> Mold Direct Exam <input type="checkbox"/> Allergens
		Asbestos in Air	Gravimetric	Miscellaneous	Sub-Contract
		<input type="checkbox"/> PCM <input type="checkbox"/> PCM-B Rules	<input type="checkbox"/> Total Dust NIOSH 0500 <input type="checkbox"/> Resp. Dust NIOSH 0600	<input type="checkbox"/> Silica FTIR (7602) <input type="checkbox"/> _____	<input type="checkbox"/> TEM Chatfield <input type="checkbox"/> TEM AHERA <input type="checkbox"/> TEM 7402 <input type="checkbox"/> Silica XRD (7500)

Sample #	Date Sampled	Time Sampled	Sample Identification (Employee, Bldg, Material, Type ¹)	Wipe Area	Time ²		Flow Rate ³		Total Air ⁴
					Start	Stop	Start	Stop	
B20-DW1	7/28/23		Drywall / joint compound						
B20-DW-2	7/28/23		Drywall / joint compound						

For Aqueous and Solid samples ensure enough sample is sent for duplicate and spike analysis

¹Type: A=Area, B=Blank, P=Personal, E=Excursion ²Beginning/End of Sample Period ³Liters/Minute ⁴Volume in Liters [time in min x flow in L/min]

Relinquished By: J. Ilich Signature: [Signature] Date/Time: 7/28/23

! ALL SHADED FIELDS MUST BE FILLED TO AVOID DELAYS !

State of Ohio
Environmental Protection Agency
Asbestos Program

Asbestos Hazard Evaluation Specialist

**John L.
Ilich**



207 Robin Hood Drive
Irwin PA 15642



Certification Number Expiration Date

ES34450

9/12/22

DOB: 1/28/71

**Card not Valid
if Altered**

United States Department of Commerce
National Institute of Standards and Technology



Certificate of Accreditation to ISO/IEC 17025:2017

NVLAP LAB CODE: 101143-0

AMA Analytical Services, Inc.
Lanham, MD

*is accredited by the National Voluntary Laboratory Accreditation Program for specific services,
listed on the Scope of Accreditation, for:*

Asbestos Fiber Analysis

*This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2017.
This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality
management system (refer to joint ISO-ILAC-IAF Communique dated January 2009).*

2022-07-01 through 2023-06-30

Effective Dates



A handwritten signature in blue ink, which appears to read "Dana S. Gorman".

For the National Voluntary Laboratory Accreditation Program

SCOPE OF ACCREDITATION TO ISO/IEC 17025:2017

AMA Analytical Services, Inc.
4475 Forbes Blvd.
Lanham, MD 20706
Mr. Andreas Saldivar
Phone: 301-459-2640 Fax: 301-459-2643
Email: andreas@amalab.com
<http://www.amalab.com>

ASBESTOS FIBER ANALYSIS


NVLAP LAB CODE 101143-0

Bulk Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A01	EPA -- 40 CFR Appendix E to Subpart E of Part 763, Interim Method of the Determination of Asbestos in Bulk Insulation Samples
18/A03	EPA 600/R-93/116: Method for the Determination of Asbestos in Bulk Building Materials

Airborne Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A02	U.S. EPA's "Interim Transmission Electron Microscopy Analytical Methods-Mandatory and Nonmandatory-and Mandatory Section to Determine Completion of Response Actions" as found in 40 CFR, Part 763, Subpart E, Appendix A.



For the National Voluntary Laboratory Accreditation Program